

专业金相检测报告样例

Metallographic report sample

40Cr | 29.00 mm | 100X / 500X

提供条件 / Availability

带金相图片的专业金相检测报告，仅在客户指定需要时提供。

Professional metallographic reports with micrographs are provided only when specifically requested by the customer.

独立样例 / Separate example

本报告属于另一材质和另一客户项目，与 C10C 质量追溯样例不是同一客户、订单或炉批。不得将其中的图片和结论套用于 C10C 或其他产品。

This 40Cr report belongs to a different material and customer project. It is not the same customer, order or heat as the C10C traceability sample. Its images and findings must not be applied to C10C or other products.

本样例保留原报告的 100X、500X 金相图片及检测结果；客户、报告编号、日期、联系方式和签章已脱敏。该报告原文记录“未发现脱碳，球化组织5级”，仅代表该样品。

The original 100X and 500X micrographs and findings are retained. Customer, report identifier, date, contacts and signatures/seals are redacted. Results refer only to the reported sample.

本文件仅用于说明报告形式与检测资料内容，不用于订单验收、材料认证或产品放行。签章遮除覆盖的文字区域不作内容补绘。

40Cr metallographic report - separate redacted sample

Micrographs provided only on specific customer request.



睿雄金属制品(芜湖)有限公司
Creation Metal (WuHu) Co.,Ltd.

金相检验报告

Inspection certificate


证书编号

Certificate No.

产品名称 Commodity	CHQWire冷墩线	牌号 Grade	40Cr	工艺 Process	PSASAIP
客户名称 Customer		订单编号 Order No.		规格 Size	29.00mm
检测项目 Test items	金相 Metallography	检测设备名称 Testing	金相显微镜 Microscope	金相等级	5级 (85-90%)
腐蚀剂 Corrosive	4%硝酸酒精	放大倍数 Zoom multiple	100X, 500×	试验日期 Test Date	



100X



500X

检测结果：未发现脱碳，球化组织5级

测试标准：

Standard test

GB/T 224脱碳层试验，GB/T 13298显

中钢碳球化组织及评级

兹证明本表所列产品，均依材料标准制造及试验，并符合标准
We hereby certify that material described herein has results in accordance with the requirements of the ab

tested with satisfactory
ion & P.O.

报告编写

Report owner

A